



J. M. Engineering Co.

A collage of images related to engineering and manufacturing, including a cable, an airplane, a building, a circuit board, and various tools and components.

# PRODUCTS

A light gray world map background.

## Heat Shrink Sleeves

### Heat Shrinkable Tapes



**Visit Us**

Manhar Bldg., 3rd Floor, 177,  
Lohar Chawl, Mumbai –  
400002, Maharashtra (INDIA)



**Email Us**

[info@jmenggco.in](mailto:info@jmenggco.in)



**Call Us**

T: +91-22-2206 1671  
F: +91-22-2209 0291



# WRSJD

## Adhesive Lined Cross-Linked Polyolefin Heat Shrink Tape

Adhesive lined, heat shrink duct and vacuum tape specifically designed for sealing joints on spiral, flexible or flat oval ducts used in heating, ventilating, air conditioning and exhaust recovery systems



### Features

- Eliminates air leakage in vacuum and ventilation systems
- Seals against moisture ingress and other contaminants
- Powerful adhesive bonds to galvanized steel, Aluminum and stainless steel
- Effective, reproducible seal allows for resistance to bending, vibrations and other mechanical stresses over a wide range of temperatures
- Application procedure is quick, simple and clean
- Continuous operating temperature: -45 - 125
- Fully shrink temperature: 120
- Color: Black, Red, Green, Yellow



### Dimensions

Order Number	Width	Wall Thickness	Standard Length(m)
WRSJD-0825	25	0.80±0.10	5,10
WRSJD-0850	50	0.80±0.10	5,10
WRSJD-08100	100	0.80±0.10	5,10
WRSJD-1025	25	1.00± 0.10	5,10
WRSJD-1050	50	1.00± 0.10	5,10
WRSJD-10100	100	1.00± 0.10	5,10

### Technical Data

Property	Test Method	Standard	Typical Performance
Tensile Strength(MPa)	ASTM D2671	10.4	11.5
Elongation(%)	ASTM D2671	300	450
Tensile Strength after aging (MPa)	UI224 158 X168hr	7.3	8.5
Elongation after aging(%)	UI224 158 X168hr	200	350
Dielectric strength(kv/mm)	IEC243	15	17.5
Volume resistivity( .cm)	ASTM D876	1X10 <sup>14</sup>	2.5X10 <sup>14</sup>

### Adhesive

Property	Test Method	Standard
Water Absorption	ASTM D570	0.2%
Softening Point( )	ASTM E28	95
Strength of pearing(PE)	ASTM D 1000	120N/25mm
Strength of pearing(AL)	ASTM D 1000	80N/25mm